

November 28, 1930.

SOUND ABSORPTION COEFFICIENTS OF THE MORE COMMON MATERIALS.

The following figures have been obtained at the Bureau of Standards for the sound absorption coefficients of a number of materials now on the market as acoustic correctives. Figures are also given for the absorption of an audience seated in chairs of different kinds. The results have all been obtained by the reverberation method.

It is not necessarily the case that the materials of highest coefficient are the most advantageous. When there is room enough to apply the requisite quantity, a material of low coefficient will give better results than one of higher absorption, due to the more uniform distribution of material. For these reasons it is advisable in drawing up specifications for auditoriums to lay emphasis upon the reverberation time desired rather than upon coefficient of material. See Bureau of Standards Circular No. 380 entitled Architectural Acoustics, which may be obtained of the Superintendent of Documents, Government Printing Office, Washington, D.C., for five cents (stamps not accepted).

<u>Material</u>	Absorption Coefficient for					<u>Date</u>
	Frequencies					
	<u>128</u>	<u>256</u>	<u>512</u>	<u>1024</u>	<u>2048</u>	
ACOUSTEX, 1" thick, spray painted.	.16	.24	.51	.71	.72	1930
ACOUSTEX, 1 1/2" thick, spray painted	.22	.31	.59	.73	.73	1930
ACOUSTIC LIME PLASTER, Finishing Lime Assoc. of Ohio, 3/4" thick	.17	.23	.28	.36	.64	1930
ACOUSTOLIC (Maftex) nailed on 2x4's, spaced 2 ft. on centers Without surface treatment	.44	.24	.31	.44	.48	1930
Tinted with water soluble aniline color		.29	.28	.41		1930
Tinted with water color paint	.40	.33	.31	.38	.37	1930
AKOUSTOLITH TILE, Grade D, 1" thk.	.08	.13	.25	.54	.67	1930
" " " D, 2" "	.15	.26	.59	.74	.52	1930
" " " B, 1" "	.10	.14	.28	.65	.73	1929
" " " C, 1 1/2" "	.12	.19	.44	.61	.66	1930
" " " C, 2" thk.	.19	.26	.53	.64	.70	1930
ARBORITE, on 13/16" x 2" furr- ing strips, spaced 12" on centers Low density material, sanded surface	.21	.48	.34	.31	.41	1930
Regular material, sanded surface	.16	.40	.27	.29	.39	1930
BALSAM WOOL, 1" thick, scrim facing	.18	.36	.55	.65	.67	1928
CELOTEX, Type B	.16	.26	.40	.62	.64	1928
" " BB	.19	.42	.61	.72	.76	1928
" " BB painted	.19	.34	.63	.75	.77	1930
FLAXLINUM, 1" thick	.09	.31	.62	.77	.69	1930
" in TMB Tile, on 13/16" x 2" furring strips, spaced 16" on centers						
1/2" Flaxlinum	.11	.19	.58	.68	.69	1930
1" Flaxlinum	.17	.34	.61	.72	.68	1930
1/2" and 1" Flaxlinum	.32	.46	.67	.69	.71	1930
2 1" layers "	.41	.59	.70	.72	.74	1930
HACHMEISTER-LIND Acoustic plaster, stippled with pins 1/2" deep	.16	.19	.25	.36	.44	1930
LAMINATED ACOUSTIC TILE (Thomas Moulding Co.)						
1" thick	.14	.26	.54	.68	.75	1930
1 1/2" thick	.22	.37	.60	.72	.76	1930

<u>Material</u>	Absorption Coefficient for					<u>Date</u>
	Frequencies					
	<u>128</u>	<u>256</u>	<u>512</u>	<u>1024</u>	<u>2048</u>	
MACOUSTIC PLASTER, stippled 1/2" thick	.09	.14	.22	.27	.41	1929
MACOUSTIC PLASTER, 1/2" thick stippled with large pins, perforations 1/2" deep	.12	.20	.31	.39	.58	1929
NASHKOTE A, 1/2" thick	.05	.13	.25	.26	.20	1929
" A, 3/4" "	.09	.16	.27	.30	.23	1929
" A, 1" "	.12	.20	.33	.33	.28	1929
" B-332, 1/2" thick	.09	.15	.31	.52	.74	1929
" B-332, 3/4" "	.12	.21	.40	.63	.81	1929
" B-332, 1" "	.19	.26	.51	.73	.89	1929
REVERBOLITE, stippled with large pins, 1/2" thick	.07	.15	.34	.47	.65	1930
SANACOUSTIC TILE, Rock Wool filler, 1 1/4" thick	.17	.41	.82	.94	.85	1930
SOUNDEX, 1 3/16" thick, spray painted	.10	.22	.36	.53	.72	1929
SOUNDEX, 1 7/16" thick, spray painted	.21	.26	.48	.68	.75	1929
THERMATEX, on 13/16" x 2" furring strips, spaced 12" on centers	.30	.39	.34	.43	.53	1930
U. S. GYPSUM TILE, 3/4" thick	.13	.28	.61	.73	.73	1930
" " " 1" "	.18	.38	.64	.73	.73	1930

The coefficients given in the above table represent the fractional part of the energy of a sound wave which is absorbed at each reflection.

Audience seated in chairs of various types.

A = cane seat chairs, open back

B = theatre chairs, box spring seat, heavily padded back

C = same as B, but single layer of padding on back

D = Church pews, seating five.

Absorption per person ⁽²⁾	Frequencies				
	128	256	512	1024	2048
Women without coats, A	0.7	1.3	2.3	3.6	4.6
Women with coats, A	1.3	2.4	4.0	5.8	6.7
Men without overcoats, A	1.3	2.1	4.1	5.5	7.4
Men with overcoats, A	2.3	3.2	4.8	6.2	7.6
Mixed audience, B			3.9	4.7	
Empty seat, B		3.4	3.0	3.3	3.6
Mixed audience, C		3.5	4.1	4.9	4.2
Empty seat, C		3.0	2.5	2.9	3.1
Mixed audience, D		2.7	3.3	3.8	3.6

(2)

These figures are numerically equal to the number of square feet of a material having unit absorption, which would absorb the same amount of sound energy.